

PRODUCT DATA SHEET

DESCRIPTION

Toray Cetex® TC1225 is a high-end thermoplastic composite material, utilizing a semi-crystalline engineered PAEK resin for excellent mechanical performance. The distinctive value of Toray Cetex® TC1225 over other composites with a PAEK family matrix is its superior processability due to a low melt viscosity and reduction in processing temperature by 50–75°C (122–167°F)*. Toray Cetex® TC1225 doesn't only yield a high-quality product used in ATL/AFP processes, it speeds up cycle times enabling cost-efficient production in all available formats.

Additionally, Toray Cetex® TC1225 is an ideal composite to be overmolded with neat or short fiber reinforced PEEK resin, creating a very strong bond. Overmolding, integrating continuous fiber reinforced composites in an injection molding process, combines the strength of high-end composites with the design freedom and complexity of injection molding parts.

Toray Cetex® TC1225 is available as a UD tape, a fabric prepreg, and as reinforced thermoplastic laminates (RTLs) of varying thicknesses. RTLs can be equipped with lightning strike protection, and carbon reinforced RTLs can be supplied with a thin glass top layer to protect a partly metallic assembly against galvanic corrosion. Glass scrim is also applicable in structures made from UD tape.

*Standard PEEK processes at temperatures up to 400°C (752°F)

FEATURES

- ▶ Superior processability as a result of low melt viscosity and relatively low processing
- ▶ Form freedom—suited for overmolding with neat or short fiber reinforced PEEK
- ▶ Relatively low processing temperature enables shorter cycle times and less energy consumption
- ▶ Excellent mechanical performance, also at elevated temperatures
- ▶ Excellent toughness and Compression After Impact (CAI) resistance of 314 MPa (45.6 ksi)
- ▶ Very low moisture absorption
- ▶ Outstanding chemical and solvent resistance
- ▶ Indefinite shelf life at ambient temperature storage
- ▶ Excellent FST performance

PRODUCT TYPE

Engineered PAEK (PolyArylEtherKetone) Thermoplastic Resin System

TYPICAL APPLICATIONS

- ▶ Primary and secondary aircraft structures
- ▶ High load aircraft interiors applications
- ▶ Access panels, rib stiffeners, brackets
- ▶ Medical
- ▶ Oil and gas

TYPICAL NEAT RESIN PROPERTIES

Density (specific gravity)	1.30 g/cm ³ (81.2 lb/ft ³)
T _g (glass transition)	147°C (297°F)
T _m (melt)	305°C (581°F)
T _c (crystallinity)	263°C (505°F)
T _p (processing)	320–380°C (608–720°F)

SHELF LIFE

Out Life:	Indefinite at ambient temperature storage
Frozen Storage Life:	Not applicable—product does not require freezing



Contact us for more information:

North America/Asia/Pacific

e explore@toraytac-usa.com

t +1 408 465 8500

Europe/Middle East/Africa

e explore@toraytac-europe.com

t +31 (0) 548 633 933

Cetex®

TC1225_PDS_v4_2019-07-03

Page 1/4

PRODUCT DATA SHEET

PHYSICAL PROPERTIES

Property	Standard Modulus Carbon UD Tape	5 Harness Satin (T300JB Carbon Woven Prepreg)	8 Harness Satin (EC6 Glass Woven Prepreg)
Fiber areal weight (FAW)	145 g/m ² (4.28 oz/yd ²)	280 g/m ² (8.26 oz/yd ²)	300 g/m ² (8.85 oz/yd ²)
Weight per ply (PAW)	221 g/m ² (6.52 oz/yd ²)	489 g/m ² (14.42 oz/yd ²)	454g/m ² (13.39 oz/yd ²)
Resin content by weight (RC)	34%	42%	34%
Consolidated ply thickness (CPT)	0.14 mm (0.0054")	0.31 mm (0.0122")	0.24 mm (0.009")
Density	1.59 g/cm ³ (99.3 lb/ft ³)	1.53 g/cm ³ (95.51 lb/ft ³)	1.92 g/cm ³ (119.8 lbs/ft ³)

MECHANICAL PROPERTIES

Standard Modulus Carbon 145gsm UD Tape 34% RC				
Property	Condition	Test Method	Results	
Tensile Strength 0°	RTD	ASTM D 3039	2410 MPa	350 ksi
Tensile Modulus 0°	RTD	ASTM D 3039	135 GPa	19.5 Msi
Tensile Strength 90°	RTD	ASTM D 3039	86 MPa	12.5 ksi
Tensile Modulus 90°	RTD	ASTM D 3039	10 GPa	1.4 Msi
Compression Strength 0°	RTD	ASTM D 6641	1300 MPa	189 ksi
Compression Modulus 0°	RTD	ASTM D 6641	124 GPa	18 Msi
In-Plane Shear Strength	RTD	ASTM D 3518	152 MPa	22 ksi
In-Plane Shear Strength 2% Offset	RTD	ASTM D 3518	42.0 MPa	6.1 ksi
In-Plane Shear Modulus	RTD	ASTM D 3518	4.3 GPa	0.62 Msi
Flexural Strength 90°	RTD	ASTM D 790	152 MPa	22 ksi
Interlaminar Shear Strength (SBS) 0°/90°	RTD	ASTM D 2344	96.5 MPa	14 ksi
Open-Hole Tensile Strength	RTD	ASTM D 5766	448 MPa	65 ksi
Open-Hole Tensile Strength	CTD	ASTM D 5766	448 MPa	65 ksi
Open-Hole Compression Strength	RTD	ASTM D 6484	310 MPa	45 ksi
Open-Hole Compression Strength	ETD	ASTM D 6484	262 MPa	38 ksi
Compression After Impact Strength 30.5 J (270 in/lb) Impact Energy	RTD	ASTM D 7137	310 MPa	45 ksi
Mode I Interlaminar Fracture Toughness (G _{IC} Strain Energy Release Rate)	RTD	ASTM D 5528	2.1 kJ/m ²	12.0 lb/in
Mode II Interlaminar Fracture Toughness (G _{IIc} Strain Energy Release Rate)	RTD	ASTM D 7905	2.6 kJ/m ²	15.0 lb/in

CTD is 18°C (65°F)
ETD is 121°C (250°F)

PRODUCT DATA SHEET

Intermediate Modulus Carbon 145gsm FAW UD Tape Laminate 34% RC				
Property	Condition	Test Method	Results	
Tensile Strength 0°	RTD	ASTM D 3039	3100 MPa	450 ksi
Tensile Modulus 0°	RTD	ASTM D 3039	159 GPa	23 Msi
Tensile Strength 90°	RTD	ASTM D3039	86 MPa	12.5 ksi
Tensile Modulus 90°	RTD	ASTM D 3039	10 GPa	1.5 Msi
Compressive Strength 0°	RTD	ASTM D 6641	1300 MPa	189 ksi
Compressive Modulus 0°	RTD	ASTM D 6641	138 GPa	20 ksi
Flexural Strength 90°	RTD	ASTM D 7264	162 MPa	23.5 ksi
Interlaminar Shear Strength (SBS) 0°/ 90°	RTD	ASTM D 2344	96.5 MPa	14 ksi
Open-Hole Tensile Strength	RTD	ASTM D 5766	655 MPa	95 ksi
Open-Hole Compressive Strength	RTD	ASTM D 6484	303 MPa	44 ksi
Compression After Impact Strength 30.5 J (270 in/lb) Impact Energy	RTD	ASTM D 7137	338 MPa	49 ksi
Fiber type IM7				

PRODUCT DATA SHEET

High Strength T300JB 3K Carbon 280gsm 5HS Woven Fabric Reinforced Laminate 42% RC				
Property	Condition	Methods	Results	
Tensile Strength 0°	RTD	EN 2597B	805 MPa	117 ksi
Tensile Modulus 0°	RTD	EN 2597B	58 GPa	8.45 Msi
Tensile Strength 90°	RTD	EN 2597B	739 MPa	107 ksi
Tensile Modulus 90°	RTD	EN 2597B	59 GPa	8.56 Msi
In-Plane Shear Strength	RTD	ASTM D3518	147 MPa	21.3 ksi
In-Plane Shear Modulus	RTD	ASTM D3518	4.1 GPa	0.59 Msi
Compression Strength 0°	RTD	ASTM D6641	628 MPa	91.1 ksi
Compression Modulus 0°	RTD	ASTM D6641	52 GPa	7.61 Msi
Compression Strength 90°	RTD	ASTM D6641	676 MPa	98.1 ksi
Compression Modulus 90°	RTD	ASTM D6641	53 GPa	7.62 Msi
Flexural Strength 0°	RTD	EN 2562A	1040 MPa	151 ksi
Flexural Modulus 0°	RTD	EN 2562A	60 GPa	8.76 Msi
Flexural Strength 90°	RTD	EN 2562A	879 MPa	127 ksi
Flexural Modulus 90°	RTD	EN 2562A	48 GPa	6.95 Msi
Compression After Impact Strength 30 J (266 in/lb) Impact Energy	RTD	ASTM D7137-12	314 MPa	45.6 ksi
Mode I Interlaminar Fracture Toughness (G _{IC} Strain Energy Release Rate)	RTD	ASTM D5528	2249 J/m ²	12.8 in-lb/in ²

50% fiber by volume (V_f)
The mechanical data provided are average values from a limited dataset. For additional data please contact Toray Advanced Composites.

HEALTH & SAFETY

Health and safety information on handling and processing Toray composite materials is described in the Safety Data Sheet available from Toray Advanced Composites. To obtain this or any other information about Toray Cetex® PAEK thermoplastic composite materials, contact Toray Advanced Composites.

Revised 07/2019

TC1225_PDS_v4_2019-07-03 Page 4/4

© 2019. All data given is based on representative samples of the materials in question. Since the method and circumstances under which these materials are processed and tested are key to their performance, and Toray Advanced Composites has no assurance of how its customers will use the material, the corporation cannot guarantee these properties. Toray®, (Toray) AmberTool®, (Toray) Cetex®, (Toray) MicroPly™, and all other related characters, logos, and trade names are claims and/or registered trademarks of Toray Industries Inc. and/or its subsidiary companies in one or more countries. Use of trademarks, trade names, and other IP rights of Toray Industries Inc. without prior written approval by such is strictly prohibited.



Toray Advanced Composites

18255 Sutter Blvd.
Morgan Hill, CA 95037, USA
t +1 408 465 8500

G. van der Muelenweg 2
7443 RE Nijverdal, The Netherlands
t +31 (0) 548 633 933



www.toraytac.com
explore@toraytac-usa.com (North America/Asia/Pacific)
explore@toraytac-europe.com (Europe/Middle East/Africa)