

PRODUCT DATA SHEET

DESCRIPTION

Toray RS-16 is a low temperature, low viscosity cure cyanate ester resin that can be used in wet winding, RTM, and VARTM processing. Its two-part construction allows easy and long-term storage while delivering excellent pot life. It is intended for lower temperature exposure with a moderate T_g requirement, and is an ideal system when used with different materials limiting the upper cure temperature. The system may also be cured using different combinations of cure/post cure temperatures and durations.

FEATURES

- ▶ **135°C (275°F) 2-hour curing cyanate resin with optional post cure cycles**
- ▶ **RTM resin with very low viscosity at temperature**
- ▶ **Low viscosity at elevated temperature**
- ▶ **Two part resin: Mix Ratio 100:9 Part A to Part B**

PRODUCT TYPE

135°C (275°F) Cyanate Ester RTM Resin System

TYPICAL APPLICATIONS

- ▶ RTM, VARTM, Resin Infusion, Wet Winding

SHELF LIFE

Pot Life:	3 hours 50 minutes at 75°C (167°F) 60 minutes at 100°C (212°F)
Storage Life:	12 months when stored between 4°C and 40°C Do Not Freeze (no storage below 4°C)

TYPICAL NEAT RESIN PROPERTIES

Specific Gravity	1.21 g/cc
T_g	No Post Cure: 149.4°C (300.9°F) Post Cure A: 230°C (446°F) Post Cure B: 230°C (446°F)
Viscosity at 50°C (122°F)	500 cPs
Minimum Viscosity at 122°C (251.6°F)	20 cP

T_g specimen cure: Ramp to 113°C (235°F) and hold for 4 hours, then ramp to 135°C (275°F) and hold for 1.5 hours
Post Cure A: 149°C (300°F) for 2 hours
Post Cure B: 177°C (350°F) for 2 hours



Contact us for more information:

North America/Asia/Pacific

e explore@toraytac-usa.com

t +1 408 465 8500

Europe/Middle East/Africa

e explore@toraytac-europe.com


t +44 (0)1773 530899

PRODUCT DATA SHEET


RESIN MECHANICAL PROPERTIES

Property	Condition	Method	Typical Results	
Flexural Modulus	RTD	ASTM D 7264	4.1 GPa	592 ksi
Flexural Strength	RTD	ASTM D 7264	159 MPa	23.1 ksi
Flexural Strain	RTD	Calculation	4.1%	

FB16K461-1, FB16K449-1, RS-16 Part A and B, Iso Profile 1




FB18K745 RS-16 Part A and FBK746 RS-16 Part B, Iso @ 75 C



PRODUCT DATA SHEET

FB18K745 RS-16 Part A and FBK746 RS-16 Part B, Iso @ 100 C



TORAY_RS-16_PDS_v2.1_2021-01-05 Page 3/3

© 2019-2021 Toray Advanced Composites. All data given is based on representative samples of the materials in question. Since the method and circumstances under which these materials are processed and tested are key to their performance, and Toray Advanced Composites has no assurance of how its customers will use the material, the corporation cannot guarantee these properties. Toray®, (Toray) AmberTool®, (Toray) Cetex®, (Toray) MicroPly™, and all other related characters, logos, and trade names are claims and/or registered trademarks of Toray Industries Inc. and/or its subsidiary companies in one or more countries. Use of trademarks, trade names, and other IP rights of Toray Industries Inc. without prior written approval by such is strictly prohibited.