

## PRODUCT DATA SHEET

### DESCRIPTION

Toray MicroPly™ EX-1516 cyanate ester film adhesive has been formulated to use in specific applications where low moisture absorption and/or low dielectric constant/low loss are of utmost importance. The resin system's strength and toughness when bonding solid, honeycomb, or foam core structures are comparable and often greater than high performance epoxy adhesives.

Due to the cyanate ester resin system's inherent low shrinkage during cure, bonded structures will retain less inherent stress and will therefore remain dimensionally stable during thermal cycling. This factor is of extreme importance when bonding structures for use in space. Finally, like other cyanate ester-based products, Toray MicroPly™ EX-1516 film adhesive displays low outgassing and microcracking properties to assure structural integrity even after severe environmental exposure and radiation bombardment.

### FEATURES

- ▶ **Compatible with EX-1515 prepregs**
- ▶ **Excellent dielectric properties**
- ▶ **Low outgassing**
- ▶ **121°C (250°F) cure capable**
- ▶ **Post curable for higher T<sub>g</sub>**
- ▶ **Compatible adhesive is EX-1516**

### PRODUCT TYPE

121°C (250°F) Cure Toughened Cyanate Ester Film Adhesive

### PRODUCT FORMS

Film Adhesive

### TYPICAL APPLICATIONS

- ▶ High dimensional stability space structures
- ▶ Reflectors
- ▶ Radomes and antennae
- ▶ Radar transparent structures
- ▶ Low observables
- ▶ Aircraft structures

### SHELF LIFE

<b>Out Life:</b>	21 days out life ≤ 21°C (70°F) and ≤ 60% RH
<b>Frozen Storage Life:</b>	12 months at ≤ -18°C (≤ 0°F)

Out life is the maximum time allowed at 21°C (70°F) or below and 60% or less RH before cure, after a single frozen storage cycle in the original unopened packaging at -18°C (0°F) or below for a period not exceeding the frozen storage life noted above.

### TYPICAL NEAT RESIN PROPERTIES

Moisture Pickup	0.6–0.7%
Dielectric Constant (10 GHz)	2.6–2.7
Loss Tangent (10 GHz)	0.005–0.006
Outgassing (ASTM E595)	TML = 0.23% CVCM = 0.02% WVR = 0.18%



Contact us for more information:

**North America/Asia/Pacific**

**e explore@toraytac-usa.com**

**t +1 408 465 8500**

**Europe/Middle East/Africa**

**e explore@toraytac-europe.com**

**t +44 (0)1773 530899**

**MicroPly™**

TORAY\_MicroPly\_EX1516\_PDS\_v3.0\_2020-02-28

Page 1/2

## PRODUCT DATA SHEET

### NWFG (6061 T-6 ALUMINUM)

Property	Condition	Method	Results	
Lap Shear Strength	RTD	ASTM D 1002	29.7 MPa	4.31 ksi
T-Peel	RTD	ASTM D 1876	105.6 N/25 mm	23.6 lbs/in

### UNSUPPORTED (6061 T-6 ALUMINUM)

Property	Condition	Method	Results	
Flatwise Tension	RTD	ASTM C 297	19.3 MPa	2.8 ksi
Flatwise Tension	ETD <sub>1</sub>	ASTM C 297	16.5 MPa	2.4 ksi
Flatwise Tension	ETD <sub>2</sub>	ASTM C 297	11.7 MPa	1.7 ksi
Flatwise Tension	CTD	ASTM C 297	17.2 MPa	2.5 ksi

ETD<sub>1</sub>: 82°C (180°F)

ETD<sub>2</sub>: 121°C (250°F)

CTD: -55°C (-67°F)

The above mechanical data was generated using the following cure schedule:

Ramp 1.7°C/3°F per minute from room temperature to 121°C/250°F, hold at 121°C/250°F for 5 hours.