

PRODUCT DATA SHEET

DESCRIPTION

Toray MicroPly™ RS-4A is a cyanate ester based film adhesive developed to provide good adhesive performance for core/face skin structures, co-curing, and secondary bonding.

FEATURES

- ▶ Low cure shrinkage
- ▶ Good balance of toughness and material strength
- ▶ Low moisture absorption
- ▶ Low microcracking
- ▶ Meets NASA requirements for outgassing

PRODUCT TYPE

177°C (350°F) Cure Cyanate Ester Film Adhesive

TYPICAL APPLICATIONS

- ▶ Core to Skin Bonding
- ▶ Space or Radome Honeycomb Structure

STANDARD PRODUCT CONFIGURATION

Widths from 12" to 42" available

- ▶ 0.035 psf, 106 Glass Support
- ▶ 0.065 psf, 106 Glass Support
- ▶ 0.015 psf, Unsupported
- ▶ 0.030 psf, Unsupported

TYPICAL NEAT RESIN PROPERTIES

Dielectric Constant (10 GHz)	2.98
Loss Tangent (10 GHz)	0.014
Outgassing (TML)	0.32%
Outgassing (CVCM)	0.00%
Outgassing (WVR)	0.34%
Density	1.21 g/cc
Dry T _g (DSC) with 177°C (350°F) standard cure 2 hrs	195°C (383°F)
Dry T _g (DSC) with + 232°C (450°F) post cure 1.5–2 hrs	238°C (460°F)

SHELF LIFE

Out Life: 14 days out life ≤ 21°C (70°F) and ≤ 60% RH

Frozen Storage Life: 6 months at ≤ -18°C (≤ 0°F)

Out life is the maximum time allowed at 21°C (70°F) or below and 60% or less RH before cure, after a single frozen storage cycle in the original unopened packaging at -18°C (0°F) or below for a period not exceeding the frozen storage life noted above.



Contact us for more information:

North America/Asia/Pacific

e explore@toraytac-usa.com

t +1 408 465 8500

Europe/Middle East/Africa

e explore@toraytac-europe.com

t +44 (0)1773 530899

MicroPly™

TORAY_MicroPly_RS-4A_PDS_v3.1_2026-01-30

Page 1/2

PRODUCT DATA SHEET

MECHANICAL PROPERTIES

Properties	Condition	Method	Typical Results	
Flatwise Tensile Strength ^{(1) (3)}	RTD	ASTM D 297	9.65 MPa	1.4 ksi
Single Lap Shear Strength	RTD	ASTM D 1002	28.25 MPa	4.1 ksi
Single Lap Shear Strength ⁽²⁾	ETD	ASTM D 1002	34.5 MPa	5.0 ksi


⁽¹⁾ Adhesive areal weight 317 g/m² (0.065 psf) autoclave cured 2 hours at 177°C (350°F) follow by 2 hours 218°C (425°F) post cure

⁽²⁾ ETD: is tested at 125°C (257°F)

⁽³⁾ Failure: Core; Skins: IM-7 (6K) PW/RS-3C, Core #8 Al Honeycomb

CURE PARAMETERS

- ▶ Apply vacuum, pressurize to 45 to 100 ps.
- ▶ Release vacuum after pressure is achieved
- ▶ Heat to 177°C (350°F) (5°C/+10°F) at 2°C ± 1°C/min (5°F ± 3°F/min)
- ▶ Hold at 177°C (350°F) for 2 hours (+15 min), Cool
- ▶ May be post cured at 232°C (450°F) for 2 hours if higher service temperature is required



Revised 01/2026

TORAY_MicroPly_RS-4A_PDS_v3.1_2026-01-30 Page 2/2

© 2026 Toray Advanced Composites. All data given is based on representative samples of the materials in question. Since the method and circumstances under which these materials are processed and tested are key to their performance, and Toray Advanced Composites has no assurance of how its customers will use the material, the corporation cannot guarantee these properties. Toray®, (Toray) AmberTool®, (Toray) Cetex®, (Toray) MicroPly™, and all other related characters, logos, and trade names are claims and/or registered trademarks of Toray Industries Inc. and/or its subsidiary companies in one or more countries. Use of trademarks, trade names, and other IP rights of Toray Industries Inc. without prior written approval by such is strictly prohibited.