


## PRODUCT DATA SHEET

### DESCRIPTION

Toray PMC CFRT® (BW-1000/Reemay) is a reinforced thermoplastic composite laminate. It blends the benefits of a thermoplastic polymer matrix with woven carbon and glass fibers in a basket weave for enhanced shapes and performance. The BW-1000/Reemay style laminate is available in a dual-layer product; carbon in one direction and glass fibers in at a 90° orientation to carbon laminated over a layer of polyester fiber. The BW-1000/Reemay laminate is thin, lightweight, and resilient for improved energy return.

### FEATURES

- › Basket weave of carbon and glass fibers
- › Bi-directional reinforcement with additional polyester fiber layer
- › Lightweight, thin, dual-layer
- › Available in various colors



### PRODUCT TYPE AND COMPOSITION

Carbon fiber content: 22%  
Glass fiber content: 22%  
Polyester fiber content: 9%  
Modified PMMA thermoplastic resin: 47%  
(Noted: Percentages are by volume and are nominal values)

### TYPICAL APPLICATIONS

- › Footwear
- › Recreational equipment
- › Skates

### SHELF LIFE

Stable indefinitely at 25°C (77°F)

Materials must be dried prior to heating and thermoforming. Please refer to the TPMC Processing Instructions.


### MATERIAL PARAMETERS

Specific Gravity	1.6 ± 0.15 (calculated based upon material volume)
Thickness	1.20 mm (± 0.2 mm)
Size	Cut to customer specifications from sheet of 91 x 122 cm (36 x 48 inches)
Standard Colors	Silver, Charcoal, and Black
Forming Temperature	195° to 200°C (383°F–392°F)
Bonding Temperature	55°C to 60°C (131°F–140°F)



Contact us for more information:  
**e** [contact@toraypmc.com](mailto:contact@toraypmc.com)  
**t** +1 805 482 1722 (USA)

## PRODUCT DATA SHEET



## MECHANICAL PROPERTIES

Properties	Method	Results
Flexural Rigidity	ASTM D790-10	> 85 N-cm
Flexural Strength	ASTM D790-10	> 170 MPa
Flexural Modulus	ASTM D790-10	> 7000 MPa

Revised 04/2019

Toray(BW-1000 Reemay)\_DS\_v6\_2019-04-24 Page 2/2

© 2019. All data given is based on representative samples of the materials in question. Since the method and circumstances under which these materials are processed and tested are key to their performance, and Toray Performance Materials Corporation has no assurance of how its customers will use the material, the corporation cannot guarantee these properties. Toray®, (Toray) CFRT®, and all other related characters, logos, and trade names are claims and/or registered trademarks of Toray Industries Inc. and/or its subsidiary companies in one or more countries. Use of trademarks, trade names, and other IP rights of Toray Industries Inc. without prior written approval by such is strictly prohibited.